



Don Baudrand, *Don Baudrand Consulting*, e-mail: donwb@tscnet.com

ELECTROLESS PLATING PROCESSES

Developing Technologies for Electroless Nickel, Palladium and Gold

Introduction

Electroless plating has become somewhat commonplace in the world of certain types of electronic devices such as hybrid circuits, multi-chip modules, capacitor, resistors, and on the chips (semiconductors) for selective metallization for conductors, via hole filling and solder bumps used to mount chips, pins and connect circuits. Electroless nickel has wide acceptance for hardware applications. Electroless plating of palladium, and gold are used more every day for special applications.

Electroless nickel

Electroless nickel has many forms. Examples are: Nickel phosphorus having differing phosphorus (P) content. The physical, electrical and surface characteristics are different for each level of phosphorus. In addition, the reaction to heat treat conditions differ widely. It is well known that heating nickel phosphorus deposits to temperatures of 300 degrees C to 400 degrees C cause the formation of nickel phosphide which hardens the deposit the degree of hardening depends on the amount of P and the heat treat temperature and time. For example, low P deposits (3-4%) heat treat to a harder value and at a lower temperature than high P (10.5-12%) deposits. Nickel phosphorus plating solutions can also host alloying metals which further change the deposit characteristics. Sometimes as little as 1/2 ppm can cause a profound change. Nickel (B) boron deposits have different characteristics from those of nickel P deposits. Similarly, nickel boron deposit characteristics change with boron content. Low B deposits are best suited for most applications. A nickel boron deposit containing 0.25% B has a melting point of 1455 degrees C. Nickel P with 11wt.% P melts at 880 degrees C. (a eutectic alloy) Numerous papers have been published and presented at conferences dealing with the virtues of electroless nickel for many engineering and hardware applications. Hardness, wear resistance and corrosion protection are characteristics which make electroless popular. The ability to plate uniform thickness over all surfaces enhance these characteristics. One place where advanced applications are found is in the electronics industry.

Electronic microcircuits and packaging requires a suitable barrier layer which can sustain a long period of service. Nickel has the slowest dissolution rate in solder and the slowest intermetallic compound formation rate compared with gold, silver, copper palladium or cobalt. Electroless nickel serves both functions well.

Let us examine what happens to electroless nickel phosphorus when it is heated under certain conditions. "Nickel P starts to oxidize about 400 degrees C and above 800 degrees D, decomposition of phosphorus and evaporation of phosphorus from the coating Occurs. Above 600 degrees C migration of phosphorus to the surface and formation of phosphorus oxide has been observed.. A kinetic study at 800 to 1000 Degrees C showed that a Ni-P deposit oxidized about 100 times faster than pure nickel. The addition of even a small amount of boron to the deposit decreased the amount of oxidation. Phosphorus in the Ni-P coating is the cause of the poor oxidation resistance of the alloy and the much purer Ni-B coatings may be expected to have a much improved resistance to oxidation."

(1) Heating nickel-P deposits in air or in moist hydrogen results in removal of phosphorus from the surface of the deposit making it much more solderable, brazable and wire bondable. It is interesting that moist hydrogen atmosphere is reducing for nickel but oxidizing for phosphorus.

Ohmic contacts are made to thick film deposits on ceramic semiconductors by the use of electroless nickel and heat treat processes. Thick film conductors of gold, silver platinum etc. have DC resistivity which is several orders of magnitude higher than calculated values. Stable low resistance ohmic contacts having ease of solderability and reliable lead attachments using heat treated nickel-P alloys. This technique can be used to make Ohmic contacts to intermetallic compounds such as gallium arsenide, thermoelectric semiconductors, bismuth-telluride, silicon and ceramic materials. Heat treating to 350 -400 degrees C for 10-15 minutes provides the improved contact. if air oxidation increased the resistance, re-heating will restore the good Ohmic contact characteristics. (2)

Electroless nickel Phosphorus for die bonding requires a heat excursion above 700 degrees C, usually about 800 degrees C in Nitrogen/hydrogen for atmosphere for 8-10 minutes, leaves a nearly pure nickel surface that when gold plated will alloy for the formation of a nickel silicide thereby giving rise to an excellent die bond.(3) Nickel boron can be die bonded without this thermal excursion.

Electroless Palladium

Palladium and palladium alloys have been developed as an economic alternative to gold plating. Palladium has some characteristics different from gold such a harder and deposit thermal stability. Electroless palladium is desirable because it can plate uniform thickness, electrically isolated areas and the number of parts in a given size tank can be greater than for electrodeposited palladium, and small complex configurations can be plated easily. Multi-chip modules (MCM's), Dual-in Line packages (DIP's) and other multi-layer hybrid circuits are examples. Soldering and wire bonding to palladium and electroless palladium deposits is made easier by the use of a thin gold over- plate of 1-2 millionths of an inch (0.025 -0.05 micrometers). Thin layers of palladium are as effective as thicker deposits so that 12-30

micro inches (0.3-0.75 micrometers) result in an economical process.(4) Electroless, or immersion gold completes the system for complex devices. Solderability to electroless palladium has been reported as good without a gold strike over the palladium deposit. Palladium is less soluble in solder than gold, thus soldering directly to electroless palladium eliminates the gold migration into the solder. Gold contaminated solder form a weak dull solder joint. Palladium can be plated over copper since the diffusion rate is slow. wire bonding to palladium is possible without copper migration. It is suggested that electroless palladium deposits onto ceramic sponge or other support materials could be used effectively as reaction catalysts, including automotive emission catalysts.

Most palladium is plated over a nickel deposit which enhances the protection and barrier functions.

Deposit properties of palladium

Density	11.5-12.0
Melting point	1552 C
Resistivity	6x of silver, 10.55 (Micro ohm-cm)
Hardness	100-200 Hv
Appearance	matte white, will not tarnish
Magnetic properties	Nonmagnetic (unless alloyed) Nickel and cobalt alloys are strongly magnetic

The future is good for electroless palladium. The first generation has been plagued by bath instability. As the chemistry becomes more friendly, applications will be evident. This will follow a similar development like electroless nickel, but operating problems must be corrected.

Electroless gold

The advantages of depositing gold by electroless means are well known. Intricate designs and miniaturization necessary in today's devices and more so in the future make electroless deposition mandatory to fabricate many of these devices. There is need for faster and less expensive methods for depositing the minimum required thickness of gold with characteristics necessary to be useful. Bonding characteristics are of paramount importance. Bonding includes soldering, brazing, wire bonding and die bonding. Much research has been done over the last 20 or more years to achieve these objectives. However, much additional research is still needed before a completely reliable electroless gold bath that is suitable for broad application becomes available.

There are a number of formulation types available which with careful attention to monitoring and control produce satisfactory deposits for specific applications. A variety of gold sources have been tried, including (potassium gold cyanide, the gold source for most), Gold chloride, various organic and inorganic gold compounds. Reducing agents include sodium hypophosphite, dimethylamineborane, sodium borohydride, hydrazine, and benzyl alcohol. Z. Mathe lists a larger number of gold sources and reducing agents.(5)

An example of an electroless gold plating solution is one developed by G. Ganu:

Table I

KAu(CN) ₂ 12-16 g/L
Diammonium citrate 15-20 g/L
Citric acid 1-2 g/L
Benzyl alcohol 2-4% v/v
Temperature 50-70 Degrees C
pH 4-9

plating rate is from 12-17 micro inches per hour, dependent on the concentration of benzyl alcohol and temperature (70 C). About 35 micro inches (0.87 micrometers) deposits in two hours.

Gold is first deposited by chemical replacement (also called immersion plate or galvanic displacement) then proceeds by reduction of gold at the surface and oxidation of benzyl alcohol to benzoic acid. Most electroless golds are sensitive to nickel contamination, therefore require an immersion gold strike prior to the electroless plating solution. The benzyl alcohol system appears to be successful without a gold strike.(6)

Others report a plating rate of 1.5 micrometers per hour (60 micro inches) plating rate (GEC Research Laboratories).(7)

Summary

Electroless nickel, of many types, electroless gold, electroless palladium and their alloys will find greater use in the future as technology advances, demanding different surface properties and a wider variety of deposit characteristics.

References

1. W. Tomlinson & Wilson, "The oxidation of electroless Ni-B and Ni-P coatings in air at 800 to 1000 C." Chapman and Hall Ltd UK

2. N. Gajbhiye "Ohmic Contacts By Electroless Nickel Plating."
3. J. White "The Interdiffusion of Phosphorus in Electroless Nickel Deposits" Metal Fin. August 1987.
4. I. Kadija, J. Abys, E. Kudrak, & J. Maisano, Solderability and Wire bonding Characteristics of Palladium, Palladium Nickel and Soft Gold Electrodeposits, Proceedings SURFIN93.
5. J. Bengston, MacDermid, Inc. Private communication.
6. Z. Mathe "Electroless" or Autocatalytic Gold Plating". Metal Finishing Jan. 1992.
7. G. Ganu "Electroless Deposition of Gold Using Benzyl Alcohol as Reducing Agent" Plating and Surface Finishing, August 1991.
8. H. Silman, Transatlantic Letter, April, 1985.